

EVALUATION OF ADHESIVE STRENGTH BASED ON THE INTENSITY OF SINGULAR STRESS FIELD OF SINGLE LAP JOINT

R. Li, N.A. Noda, Y. Sano, T. Miyazaki, K. Iida and Y. Takase

Department of Mechanical Engineering, Kyushu Institute of Technology, 1-1 Sensui-cho Tobata-ku,
Kitakyushu-shi 804-8550, Japan

Abstract: In this study, the adhesive strength for single lap joint is investigated based on the intensity of singular stress field. First, the critical intensity of singular stress at the adhesive dissimilar joint is calculated by using finite element method (FEM) based on the experimental result. It is found that the adhesive strength can be expressed as the critical intensity of singular stress field. Then, a suitable evaluation method of adhesive strength is investigated focusing on the intensity of singular stress field. The effect of specimen geometry on the intensity of singular stress is considered. The results show that the intensity of singular stress field decreases with increasing the adherend thickness, the minimum intensity of singular stress can be obtained when the adherend thickness is large enough. The results of the deformation angle at the interface corner edge show a similar trend as in intensity of singular stress field, and the minimum deformation angle can be obtained when the adherend thickness is large enough. The usefulness of the method is investigated focusing on the deformation angle at the interface corner edge.

Keywords: Stress intensity factor; Interfaces; Deformation angle; Single lap joint

1 INTRODUCTION

Since adhesively joints are economical, practical and easy to be used; thus they have been widely used in a variety of industries. A number of studies of adhesive joints have been made so far [1-4]. The authors investigated the adhesive butt joint strength in Fig. 1 by changing the adhesive thickness and material combination [5,6]. It is found that the adhesive strength can be expressed as the critical intensity of singular stress field as $K_{\sigma c} = \text{const}$ based on the experimental results. The adhesive strengths of the single lap joint (see Fig. 2(a)) and double lap joint (see Fig.2(b)) were also investigated previously [7]. In this result, the adhesive strength of double lap joint is not equal to the one of single lap joint as expected and is almost twice larger than the one of single lap joint. Compared with double lap joint, single lap joint testing is more stable and used conveniently. The testing method and experimental adhesive strength are prescribed by Japanese Industrial Standards (JIS) [8]. However, since the debonding strength is defined as the magnitude of the load, the strength is affected by the specimen dimension and difficult to be applied to other geometries. Therefore, it is necessary to find a suitable method to evaluation the debonding strength of single lap joint testing.

In this paper, first, the debonding strength of single lap joint will be investigated based on the experimental results [9] by using the evaluation method shown in [6]. Then, a suitable evaluation method of adhesive strength will be evaluated focusing on the intensity of singular stress field and the deformation angle appearing at the end of interface.




Fig.1 Adhesive strength expressed as $K_{\sigma c} = \text{const}$
for butt joint.




Fig.2 Single and double lap joints.

2 ADHESIVE STRENGTH EXPRESSED AS A CONSTAN CRITICAL INTENSITY OF SINGULAR STRESS K_{σ_c} FOR SINGLE LAP JOINT WITH VARYING ADHESIVE GEOMETRY l_{ad} AND t_{ad}

Figure 3 shows the schematic illustration of the analysis models. It has been reported that the singularity exists near the interface corner, and the singularity depending on the singular indexes λ_1 and λ_2 at the interface [10]. In this paper, $\lambda_1=0.6062$, $\lambda_2=0.9989$. The stress σ_θ at r direction ($\theta=0$) can be expressed as follows. The notation r denotes the radial distance away from the corner singular point O.

$$\sigma_\theta = \frac{K_{\sigma, \lambda_1}}{r^{1-\lambda_1}} + \frac{K_{\sigma, \lambda_2}}{r^{1-\lambda_2}} \cong \frac{K_{\sigma, \lambda_1}}{r^{1-\lambda_1}} (1 + C_\sigma r^{\lambda_2-\lambda_1}) \quad (1)$$

Here, K_{σ, λ_1} and K_{σ, λ_2} are the intensities of the singular stress field. The intensities of singular stress field can be obtained based on our previous study[11,12] by using Reciprocal Work Contour Integral Method[13] (RWCIM). The intensities of the singular stress field can be represented with only K_{σ, λ_1} since C_σ is almost constant expressed as $C_\sigma = -5.2387 \pm 0.2659$.

In this study, the thick specimens used by Park [9] in Fig.3 are analyzed where the adherends aluminum alloy 6061-T6 (Young's modulus $E=68.9$ [GPa], Poisson's ratio $\nu=0.3$) are bonded with adhesive FM73 M epoxy (Young's modulus $E=4.2$ [GPa], Poisson's ratio $\nu=0.45$). The typical force-displacement curves of the adhesive joints show nearly linear behavior. A drop in load was used to detect a failure. The total length of the specimen is 225mm, adherend thickness $t_1=7$ mm, $d=10$ mm, adhesive thickness $t_{ad}=0.15\sim 0.9$ mm, adhesive length $l_{ad}=20\sim 50$ mm, $L=50$ mm, $\sigma_o=1$ MPa ($P=14.15$ N).

Fig.4 shows the K_{σ_c} with different l_{ad} and t_{ad} under $P=P_{af}$. Here, P_{af} is the fracture load, "A25" means $l_{ad}=25$ mm and $t_{ad}=0.15$ mm, "A25-30" means $l_{ad}=25$ mm and $t_{ad}=0.30$ mm, and so on. It is found that the average value of K_{σ_c} is $4.030 \text{ MPa} \cdot \text{m}^{1-\lambda_1}$, and the K_{σ_c} values are almost constant independent of the l_{ad} and t_{ad} . It is seen that the adhesive strength can be expressed as $K_{\sigma_c}=\text{const}$.




Fig. 3 Analysis model and boundary condition.




Fig. 4 Adhesive strength expressed as $K_{\sigma_c}=\text{const}$ for $t_{ad}=0.15\sim 0.9$ mm and $l_{ad}=20\sim 50$ mm under fixed $t_1=7$ mm, $L=50$ mm.

3 PURE SHEAR TESTING TO MINIMIZE K_{σ, λ_1}

The butt joint in Fig.1 is used to obtain the adhesive strength under pure tension [5, 6] and the single lap joint in Fig.2 is used to obtain the adhesive strength under pure shear. However, due to the deformation of single lap joint during testing, peeling force as well as shearing force is applied to the adhesive region. Then, the intensity of singular stress K_{σ, λ_1} is also affected by the peeling force due to the deformation.

Since the single lap joint testing should be done under pure shear loading, smaller K_{σ, λ_1} is desirable. The fracture load P_{af} increases with increasing the adhesive length l_{ad} as described in [9], and the adhesive strength can be expressed as $K_{\sigma_c}=\text{const}$ independent of adhesive geometry l_{ad} and t_{ad} . This means that

when K_{σ, λ_1} is small, the fracture load P_{af} is large. Therefore, in order to minimize K_{σ, λ_1} , the effect of specimen geometry is considered under the same adhesive geometry and load P . In this section, we assume $P = 14.15\text{N}$, the adhesive length $l_{ad} = 25\text{mm}$, and adhesive thickness $t_{ad} = 0.15\text{mm}$. Then, the effects of specimen geometries t_1 (adherend thickness) and L (fixed boundary length) on the intensity of singular stress field K_{σ, λ_1} are discussed.

Figure 5 shows the relationship between the intensity of singular stress field K_{σ, λ_1} and adherend thickness t_1 under different fixed length L . The dashed line shows the minimum value of K_{σ, λ_1} . Here, JIS* means only the adherend thickness $t_1 = 1.5\text{mm}$ and fixed boundary length $L = 50\text{mm}$ in JIS K6850 are used as shown in Fig.3. As can be seen from Fig.5, the K_{σ, λ_1} decreases with increasing t_1 and L . The K_{σ, λ_1} value becomes constant if t_1 is large enough. The $K_{\sigma, \lambda_1} |_{t_1=1.5\text{mm}}$ (JIS K6850) is 5 times larger than the one of $K_{\sigma, \min}$, and the $K_{\sigma, \lambda_1} |_{t_1=7\text{mm}}$ [9] is more than twice than that of $K_{\sigma, \min}$. It is seen that the specimen in [9] is better than the JIS, but it is more desirable to use larger adherend thickness.




Fig. 5. Effect of L and t_1 on K_{σ, λ_1} under fixed l_{ad} and t_{ad} (JIS*: Only $t_1 = 1.5\text{mm}$ and $L = 50\text{mm}$ in JIS K6850 are used as shown in Fig.3).




Fig.6. Definition of deformation angle.

4 DEFORMATION ANGLE AT THE INTERFACE CORNER

As shown in section 3, the intensity of singular stress K_{σ, λ_1} decreases with increasing the adherend thickness t_1 . It is found that the minimum K_{σ, λ_1} can be obtained when t_1 is large enough. In this section, the deformation angle at interface corner is considered by changing the distance l_{θ} .

Fig. 6 shows the deformation example near the interface corners. In order to obtain the deformation angle, two target points are considered. For the deformation angle θ_{ol} at interface corner O, two target points are points O and A with the distance l_{θ} . For the deformation angle θ_{or} at interface corner O, two target points are points O and B with the distance l_{θ} . Fig. 7 shows the deformation angles θ_{ol} and θ_{or} vs. l_{θ} under $t_1 = 7\text{mm}$. It is found that the values of θ_{ol} and θ_{or} both increase with increasing l_{θ} , and the difference between θ_{ol} and θ_{or} increases with decreasing l_{θ} . Therefore, we cannot obtain the maximum deformation angle at corner O. Fig. 8 shows the deformation angle θ_c vs. l_{θ} under $t_1 = 7\text{mm}$. It is seen that the value of θ_c increases initially with increasing l_{θ} and then decreases. Then, the maximum θ_c can be obtained when $l_{\theta} = 1/3^3\text{mm}$. Thus, in this study, the deformation angle will be considered by using the maximum deformation angle at corner C rather than at corner O.




Fig. 7 Deformation angle at corner edge O.




Fig. 8 Deformation angle at corner edge C.

As can be seen from Fig. 5, the minimum K_{σ, λ_1} can be obtained when t_1 is large enough. Similar to the variation trend of K_{σ, λ_1} , the minimum θ_C can be obtained when the adherend thickness t_1 is large enough.

5 CONCLUSION

In this study, the adhesive strength for single lap joint is investigated based on the intensity of singular stress field. Since the experiments are often time-consuming and costly, the analysis method shown in this paper can help to predict the strength of adhesive joint accurately and conveniently. The conclusions can be summarized in the following way.

- (1) In this paper, the critical intensity of singular stress field K_{σ_c} is investigated by using the analysis method presented. It is seen that the adhesive strength can be expressed as $K_{\sigma_c} = \text{const}$.
- (2) The effects of specimen geometries t_1 (adherend thickness) and L (fixed boundary length) on the intensity of singular stress field K_{σ, λ_1} are discussed. The results show that the K_{σ, λ_1} at the interface corner decreases with increasing the t_1 , and the minimum intensity of singular stress field $K_{\sigma, \min}$ can be obtained when t_1 is large enough.
- (3) The deformation angle at the interface corner is investigated by using the maximum deformation angle at interface corner C. It is found that the minimum deformation angle θ_C can be obtained when the adherend thickness t_1 is large enough.

6 REFERENCES

- [1] Y. M. Jen, C. W. Ko, Evaluation of fatigue life of adhesively bonded aluminum single-lap joints using interfacial parameters, *International Journal of Fatigue*, 32(2): 330-340, 2010.
- [2] M. Y. Tsai, J. Morton, An investigation into the stresses in double-lap adhesive joints with laminated composite adherends, *International Journal of Solids and Structures*, 47(24): 3317-3325, 2010.
- [3] Li. G, P. Lee-Sullivan, R. W. Thring, Nonlinear finite element analysis of stress and strain distributions across the adhesive thickness in composite single-lap joints, *Composite Structures*, 46(4): 395-403, 1999.
- [4] M. Imanaka, K. Ishii, H. Nakayama, Evaluation of fatigue strength of adhesively bonded single and single step double lap Joints based on stress singularity parameters, *Engineering Fractures Mechanics*, 62(4-5): 409-424, 1999.
- [5] Y. Zhang, N.A. Noda, K. T. Takaishi, X. Lan, Effect of adhesive thickness on the interface of singular stress at the adhesive dissimilar joint, *Journal of Solid Mechanics and Materials Engineering*, 4(10), 2010.
- [6] N. A. Noda, T. Miyazaki, R. Li, T. Uchikoba, Y. Sano, Debonding strength evaluation in terms of the intensity of singular stress at the interface corner with and without fictitious crack, *International Journal of Adhesion and Adhesives*, 61: 46-64, 2015.

- [7] K. Ikegami, H. Kyogoku, H. Kawagoe, T. Sugibayashi, K. Nohno, T. Fujii, K. Motoie, F. Yoshida, Benchmark tests for synthetic evaluation of adhesive-joint strength (1st Report, Experimental results of butt, single-lap, double-lap joints and DCB test). Japan Society of Mechanical Engineers, 63(608): 174-181, 1997-4. (in Japanese)
- [8] JIS K6850:1999, Adhesives-Determination of tensile lap-shear strength of rigid-to-rigid bonded assemblies. (in Japanese)
- [9] J. H. Park, J. H. Choi, J. H. Kweon. Evaluating the strengths of thick aluminum -to-aluminum joints with different adhesive lengths and thicknesses, Composite Structures, 92, 2226-2235, 2010.
- [10] R. Yuuki. Mechanics of interface. Baifuukann, Tokyo, 283p, 1993. (in Japanese)
- [11] T. Miyazaki, N.A. Noda, R. Li, T. Uchikoba, Y. Sano. Debonding criterion for single lap joints from the intensity of singular stress field. Journal of Japan Institute of Electronics Packaging. 16(2): 143-151, 2013. (in Japanese)
- [12] T. Miyazaki, N. A. Noda, R. Li, T. Uchikoba, Y. Sano. Examination on a criterion for a debonding fracture of single lap joints from the intensity of singular stress field, Proceeding of 13th International Conference on Fracture: S11-029, 2013.
- [13] Carpenter, W. C. Byers C. A path independent integral for computing stress intensities for V-notched cracks in a bi-material, International Journal of Fracture, 35: 245-268, 1987.